

FASHION IMAGE AFI

POLI-FLEX® Fashion Image are transfer films with a fashionable design and unique surface finish. The ecologically inert polyurethane film has excellent washing and cleaning properties and is preferred due to a pleasant textile touch.

POLI-FLEX® Fashion Image is suitable to transfer onto textiles such as cotton, polyester/cotton blends and polyester/acrylic.

We recommend using a standard 45° blade. After weeding, the cut flex film is **transferred by heat press**. The PET liner of all POLI-FLEX® Fashion Image (4280 – 4284) products should be removed warm. We recommend evaluation on test material.

Due to the various influences which occur from production and transfer of plotter lettering, consistency of the carrier materials and also washing and cleaning conditions, product liability can only cover the unprocessed material.

Do not plotter cut and leave sitting for more than 8 hours - it will start to curl.

Christmas HTV and Black Bandana HTV note: These vinyls may appear sticky, this does dissolve and quickly disappears after being washed.



45° Blade Recommended



Cut this material in mirror image



160°C



2,5 - 3,0 bar Medium pressure



15 Seconds



Peel Warm/Cool



Wash warm (60°C) inside out. Tumble Dry normal. Do NOT dry clean.



Layering not recommended



Iron inside out. Do not iron directly onto transfers.



Suitable for cotton, uncoated polyester, poly/cotton, acrylic & similar fabrics.



Application Tape not required.

Standard dimensions: 300 - 500mm x 25m

THICKNESS

- 120 microns +/- 10 % (Carbon Fibre)
- 90 microns +/- 10 % (Camouflage)
- 90 microns +/- 10 % (Leopard)
- 90 microns +/- 10 % (Zebra)
- 90 microns +/- 10 % (Basketball)
- 90 microns +/- 10 % (Brown Leather)
- 80 microns +/- 10 % (Fashion Prints/Holiday)

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by the manufacturer.