

ALUMINIUM WINDOW Packers

FIRE RESISTANT

25 TONNE LOAD

*Manufactures recommended load.

Suitable for window
installation, door frame/
jamb installation and
more.

**PRODUCT RANGE
GUIDE**

MACSIM®



WPA

ALUMINIUM

FIRE RESISTANT



Plastic Q Pack

CODE	THICKNESS	LENGTH	COLOUR	QTY/Pack	INDIVIDUAL BARCODE
WPAQ01075	1.0mm	75mm	BRONZE	200	9312862236772
WPAQ02075	2.0mm	75mm	WHITE	200	9312862236796
WPAQ03075	3.0mm	75mm	SILVER	200	9312862236819
WPAQ05075	5.0mm	75mm	GOLD	200	9312862236833
WPAQ10075	10mm	75mm	BLACK	70	9312862236857
WPAQ01090	1.0mm	90mm	BRONZE	200	9312862236789
WPAQ02090	2.0mm	90mm	WHITE	200	9312862236802
WPAQ03090	3.0mm	90mm	SILVER	200	9312862236826
WPAQ05090	5.0mm	90mm	GOLD	125	9312862236840
WPAQ10090	10mm	90mm	BLACK	60	9312862236864

Plastic J Pack

CODE	THICKNESS	LENGTH	COLOUR	QTY/Pack	INDIVIDUAL BARCODE
WPAJ01075	1.0mm	75mm	BRONZE	100	9312862236673
WPAJ02075	2.0mm	75mm	WHITE	75	9312862236697
WPAJ03075	3.0mm	75mm	SILVER	50	9312862236710
WPAJ05075	5.0mm	75mm	GOLD	30	9312862236734
WPAJ10075	10mm	75mm	BLACK	15	9312862236758
WPAJ01090	1.0mm	90mm	BRONZE	100	9312862236680
WPAJ02090	2.0mm	90mm	WHITE	60	9312862236703
WPAJ03090	3.0mm	90mm	SILVER	35	9312862236727
WPAJ05090	5.0mm	90mm	GOLD	20	9312862236741
WPAJ10090	10mm	90mm	BLACK	12	9312862236765

MATERIAL CHARACTERISTICS

MECHANICAL PROPERTIES	VALUE
Material	6063 Grade Aluminium
Material Brand	T5
Tensile Strength	175MPa
HW	9~11HW

GB/T5237.2-2017

PHYSICAL PROPERTIES	VALUE
Density	2690kg/m ³
Melting Point	615-655°C
Thermal Expansion	24.5µm/m.K
Modulus of Elasticity	68.9GPa
Thermal Conductivity	209 W/m.K
Electrical Resistivity	32nΩ•m
Electrical Resistivity	55% IACS

GB/T5237.2-2017

PHYSICAL PROPERTIES	VALUE
Manganese (Mn)	0.1
Iron (Fe)	0.35
Copper (Cu)	0.1
Magnesium (Mg)	0.45-0.9
Silicon (Si)	0.20-0.6
Zinc (Zn)	0.1
Chromium (Cr)	0.1
Other (Each)	0.05
Others (Total)	0.15
Aluminium (Al)	BALANCE

GB/T3190-2008

Sydney (Head Office)
10 Wonderland Dr
Eastern Creek
NSW 2766
P: (02) 9881 2400
F: (02) 9881 2444

Melbourne
29 Metro Link Cct West
Campbellfield
VIC 3061
P: (03) 9495 7400
F: (03) 9495 7444

Brisbane
36-44 Arshad drive
Berrinba
QLD 4117
P: (07) 3268 5668
F: (07) 3268 6110

Townsville
4/ 13-19 Civil Rd
Garbutt
QLD 4814
P: (07) 4728 2344
F: (07) 4779 4482

Perth
42 Prosperity Ave
Wangara
WA 6065
P: (08) 9308 3800
F: (08) 9308 3880

Adelaide
Unit 4/ 53 Stanbel Rd
Salisbury Plain
SA 5019
P: (08) 8286 0410
F: (08) 8286 0414

Macsim (NZ)
5 Fisher Crescent
Mount Weillington
AUCKLAND 1060
P: (+649) 579 0801
F: (+649) 579 0802