



Quick Dry Rubberized Undercoating

4361-F, 4364-F, 60-4363-F

Quick Dry Rubberized Undercoat is a rapid-drying highly protective automotive coating for autobody interiors, underhood and underbody applications. Resists abrasion and inhibits rust as it seals out dust and moisture. Deadens sound. Excellent adhesion to painted and unpainted surfaces.



Mix Ratio

Ready to use.



Suitable Substrates

- Painted or primed steel
- Galvanized steel
- Bare steel
- Bare Aluminum
- Painted or primed aluminum



Surface Prep & Application

Aerosol: Shake well. Wash and solvent clean surface to remove all rust, dirt and grease using SCAT 6311, Speedi SCAT 6321 or Aqua SCAT 2 1391/1394. Hold can in an upright position and spray 8-10 inches from surface, using steady light strokes. 2 coats (@2.5-3.5 mils per coat) will produce a better finish than one heavy coat. Remove overspray with Acry Solvent 9783/9784.



Quart/Gallon: Stir thoroughly before use. Wash and solvent clean surface to remove all rust, dirt and grease. Apply with a shutz gun, using the gun manufacturer's recommended air pressure. Allow 15 - 20 minutes between coats. Thoroughly clean spray gun with Acry Solvent 9783/9784 immediately after use. Max temperature resistance is 250°F (121°C). NOTE: Topcoating is not recommended. This product contains asphalt which may stain light colored topcoats.



Product Specifications

Color.....	Black	Size (4361-F).....	Gallon
Shelf life.....	1 year	(4364-F).....	Quart
		(60-4363-F).....	20 oz aero

Regulatory**4361-F/4364-F**

Category	Underbody coating	Wt % of volatiles.....	55.78
VOC actual	2.74#/gal (328 g/l)	Wt % of water	0.1
VOC regulatory	3.58#/gal (429 g/l)	Wt % of exempt compound	20.08
Density	7.69 #/gal	Vol % of exempt compound	23.35

60-4363-F

Category	Undercoating
VOC content	<40% by weight

**Limitations & Precautions**

- This product provides adhesion & corrosion protection when used over noted (checked) substrates - when properly cleaned, sanded & applied.
- Visit www.tat-co.com to assure use of the most current instructions and TDS on this product.
- See website (www.tat-co.com) for this document in other languages. (Vea el web site para este documento en español. Voir le site web pour ce document en français.)
- For use only by professional, trained painters. Not for sale to or use by the general public.
- Before use, read and follow all TDS, label and SDS precautions.
- If mixed with other components, mixture may be hazards of all combined components.
- All Standard Operating Procedures (SOP) can be found on the Transtar website at www.tat-co.com.

LIMITED WARRANTY

The successful performance of this product is dependent on many factors beyond our control. Results are dependent upon the skill of the operator. This product is manufactured to meet the highest level of consistency and quality for the intended use. Transtar Autobody Technologies, Inc. warrants that its products meet the specifications which it sets for them. Should this product be proven to be off-specification within shelf life as stated in this datasheet, Transtar Autobody Technologies, Inc. will, at its sole discretion, either replace the product or issue credit for the original purchase price of the product. The replacement or refund shall be the buyer's sole remedy and Transtar Autobody Technologies, Inc. and its affiliates MAKE NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, DESIGN COMPATIBILITY AND FITNESS FOR A PARTICULAR PURPOSE. LABOR OR COST OF LABOR AND OTHER INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.