

# Technical Information

## 35- | Basecoat



### 1. Properties

Basecoat for solid-colour, metallic and pearl coatings

- High solid and pigment content – good hiding power
- Low material consumption
- Short flash off time

### 2. Application

	<b>Mixing ratio</b> 2 : 1	100% by vol.                      35- 50% by vol.                        60-10, -20, -30, -40
	<b>Spray viscosity</b> DIN 4 at 20°C	approx. 18 – 22 s
	<b>Potlife</b>	48 h for RFU mixture / 20°C
	<b>High pressure spray gun</b>	1.3 – 1.4 mm
	<b>Number of spraycoats</b> <b>Film thickness</b>	2 (spray to cover), ½ to match the effect approx. 15 – 20 µm

### 3. Flash off

	<b>Flash off at 20°C</b>	approx. 10 min., until mat
--	--------------------------	----------------------------

### Safety instructions:

**The products are suitable for professional use only.**

**It cannot be ruled out that this product contains particles < 0.1 µm.**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.