


Intended use

Mipa 2K-HS-Klarlack CS 96 is a scratch-resistant two-component HS acrylic clearcoat based on Reflow technology. Because of its resistance to micro-scratches (caused e.g. by car wash plants) and to chemicals, Mipa 2K-HS-Klarlack CS 96 is particularly suitable for high-quality partial or complete paintworks on cars, motorcycles and commercial vehicles. Mipa 2K-HS-Klarlack CS 96 is especially easy to apply and ensures optimal spray mist absorption during the application on large surfaces or at high temperatures. VOC-conform.

Spreading rate: 6,0 - 8,0 m²/l

Processing instructions**Colour**

colourless

**Mixing ratio****Hardener****by weight (lacquer : hardener)****by volume (lacquer : hardener)**

Mipa 2K-MS-Härter

–

2 : 1

Mipa 2K-HS-Härter

–

2 : 1

**Hardener****for complete paintwork****for partial paintwork**

Mipa 2K-MS-Härter MS 25 / MS 40

Mipa 2K-MS-Härter MS 10

Mipa 2K-HS-Härter HS 25 / HS 35

Mipa 2K-HS-Härter HS 10

**Pot life**


1 h with Mipa 2K-Härter MS 10 / HS 10 at 20 °C

4 h with Mipa 2K-Härter MS 25 / HS 25 at 20 °C

6 h with Mipa 2K-Härter MS 40 / HS 35 at 20 °C

**Thinner**

–

**Spray viscosity**

Ready for spraying after addition of hardener

gravity spray gun**Airmix/Airless**

18 - 21 s 4 mm DIN

–

**Application mode****Application mode****Hardener****pressure
(bar)****nozzle (mm)****spray
passes****Thinner**

gravity spray gun (high pressure)

–

2 - 2,5

1,2 - 1,3

1 - 2

–

HVLP (low pressure)

–

2 - 2,2

1,2 - 1,3

1 - 2

–

HVLP / internal nozzle pressure


–

0,7

–

–

–

**Flash-off time**

5 - 10 min between the coats

10 - 15 min before oven drying

Dry coat thickness

40 - 50 µm

**Drying time**

object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
20 °C	20 - 25 min	4 - 6 h	16 h	—	—
60 °C	—	25 - 30 min	1 h	—	—
Infrared drying shortwave	—	8 min	—	—	—
Infrared drying mediumwave	—	10 - 15 min	—	—	—

Note**Storage:** at least 3 years in unopened original container**VOC Regulation :** EU limit value for this product (category B/e): 840 g/l
This product contains max. 530 g/l of VOC.**Processing conditions:** From +10 °C and up to 80 % relative air humidity. Ensure an adequate air ventilation.**Processing instructions:** —