

10/2016

# :: Klarlack-Spray

clear-coat spray

1

## **CHARACTERISTICS**

Clear Coat Spray is a durable, high-gloss, acrylic-based transparent enamel. This all-weather product also dries quickly.

### **APPLICATION**

Clear Coat Spray can be applied to nearly all surfaces (wood, metal, acrylic paint). Not suitable for use on pure white surfaces.

### **PRODUCT DATA**

Material data: Color: transparent-shining Specific gravity: 0.751 g/mL Solids by volume: 16 % Recommended coat thickness: 75  $\mu$ m wet, 35  $\mu$ m dry Theoretical coverage: 400 mL = 1-2 m<sup>2</sup> Drying time (20°C): Approx. 60 minutes Recoat time (20°C): 10 minutes or when hardened (2-3 hours) stability in storage (20°C): 36 month

### HANDLING

The surfaces to be coated must be clean, dry, and free of rust, grease and oil. Shake the spray can well for at least 3 minutes before use. Spray from approx. 20-30 cm (10-12 in) away from the surface. Apply thin coats in steady, even up-and-down and side-to-side movements.

VOSSCHEMIE GMBH Esinger Steinweg 50 D-25436 Uetersen Telefon +49 (0) 4122/717 -0 Telefax +49 (0) 4122/717-158 E-Mail info@vosschemie.de www.carsystem.org www.vosschemie.de





10/2016

#### PRECAUTIONS

Contents under pressure. Do not store at temperatures above 50°C.

### **SAFETY ISSUES**

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE

VOSSCHEMIE GMBH Esinger Steinweg 50 D-25436 Uetersen

www.carsystem.org www.vosschemie.de

