



▶ DPF 510G/M Vinyl Film

Digital Print Pressure-Sensitive Vinyl Film

DPF 510G/M is a 3.2-mil (80 micron) calendered film with a clear, solvent-based pressure-sensitive adhesive. The two-sided polycoated liner provides excellent lay-flat properties. The high-quality adhesive provides far superior adhesion and cohesion properties than water-based adhesive. DPF 510 is available in a white gloss finish (DPF 510G) and white matte finish (DPF 510M). DPF 510 is rated for outdoor durability up to 3 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Short-term promotional and display graphics, including kiosks, POP displays and real estate signage.
- Excellent printability on Eco-Solvent, Solvent and Latex print systems.
- Ideal for interior and exterior applications on flat surfaces.

Certified for
HP Latex Inks

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	70 to 90 Gloss Units (Gloss) Up to 30 Gloss Units (Matte)	
THICKNESS	Micrometer, Federal Bench Type	3.2-mil (80 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 15.0 lb/in	≥ 2.7 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 200%	
SHELF LIFE (IN BOX)	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	50°F to 90°F	10°C to 32°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-20°F to 150°F	-29°C to 65°C
DIMENSIONAL STABILITY	158°F (70°C), 48 hours	10-mil	0.25 mm
PEEL ADHESION	PSTC-1, 15 min, 70°F (21°C)	≥ 2.00 lb/in	≥ 0.36 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	40 g/2 in	7.9 g/cm

Standard Terms & Conditions Apply

USA
 a 200 Boysenberry Lane, Placentia, CA 92870
 p 800 232 7161 / +1 714 985 6300
 f +1 714 985 6305

EUROPE
 a Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
 p +31 70 354 4311
 f +31 70 355 7721

CHINA
 a No. 1989 Xinchang Road, Weifang, Shandong, 262400
 p +86 0536 6226568




TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:




All orders and purchases made in connection with this document are governed and limited by Arlon's Standard Terms and Conditions, which are incorporated in full by this reference and are available at <http://www.arlon.com/terms-and-conditions> or in hardcopy by request.

May 2020



USA

-  200 Boysenberry Lane, Placentia, CA 92870
-  800 232 7161 / +1 714 985 6300
-  +1 714 985 6305

EUROPE

-  Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
-  +31 70 354 4311
-  +31 70 355 7721

CHINA

-  No. 1989 Xinchang Road, Weifang, Shandong, 262400
-  +86 0536 6226568