

# SUBLITHIN MATT LT

## SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	110 microns	Non adhesive polyester	<p>OEKO-TEX® CONFIDENCE IN TEXTILES <b>STANDARD 100</b> 14CX00052 CENTROCOT</p> <p>REACH n° 1907/2006/EU</p> <p>VEGANOK AZIENDA N. 1004</p> <p>Certified for HP Latex Inks</p>

## APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
textiles colored with sublimation inks	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	80 gf	20 cm/sec	15 seconds	135°C (275°F)	Medium (2,5 bar)	hot

- Print, Cut and peel off excess material
- Remove the print from the support with the help of TTD Easy
- Place the decoration on the fabric
- Apply following the recommended parameters
- Remove the TTD while hot

### PRODUCT HIGHLIGHTS

- Anti migration barrier
- Suitable for sublimation dyed fabrics
- Low temperature transfer

**NOTE:** Given the large number of sublimation inks and printers, we highly recommend to perform a test before launching a production

## CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	NO	NO	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on [www.siser.com](http://www.siser.com). For further information, please contact our sales office: [info@siser.it](mailto:info@siser.it)



Siser s.r.l.  
Viale della Tecnica, 18  
36100 Vicenza - Italy

Tel. +39 0444.287960  
Fax +39 0444.287959  
[info@siser.it](mailto:info@siser.it)  
[www.siser.com](http://www.siser.com)

r.e.a. vi 171856  
reg. imp. vi n° 14971  
c.s. € 103.300 i.v.  
p.iva 01591490246



Management System  
ISO 9001:2015  
ISO 14001:2015  
[www.tuv.com](http://www.tuv.com)  
ID 9105027968

